



## TECHNICAL SPECIFICATIONS

### AB-2102

**SPECIFICATION ASTM D2000: 2AA607A13**

**POLYMER: Styrene-Butadiene (SBR)**

ASTM	DESCRIPTION	VALUE
	SPECIFIC GRAVITY (gr/cc)	1.33
D2240	HARDNESS (Shore A)	60
D412	TENSILE (psi)	700 min.
	ELONGATION (%)	250 min.
D395B	COMPRESSION SET	22 hrs @ 70°C 50% max.
D573	HEAT AGING	70 hrs @ 70°C Changed : Hardness: ±15 points max. Tensile: ±30% max. Elongation: -50% max.
Temperature Range (general guideline):		-20° to 180°F (-29° to 82°C)
Mullen Burst 1Ply: 300 psi nom.		
Maximum pieces per roll: 2		
Minimum piece length: 10'		
Width tolerance: -0 /+ 1"		
Length tolerance: ± 10%		
Material is within RMA commercial gauge tolerances.		

**Please ensure the product meets your application specification prior to order placement.**

